

## Absorption Coefficients of Rockwool Slabs



**Absorption Coefficient and Weighed Sound Absorption Coefficient:  $\alpha_w$  of Rockwool Tissue Faced Slabs**

Product	Freq. Hz (Third Octave Bands)																		aw
	100	125	160	200	250	315	400	500	630	800	1k	1.25k	1.6k	2k	2.5k	3.15k	4k	5k	
RWA45 – 50mm	0.10	0.10	0.26	0.38	0.54	0.72	0.83	1.00	1.08	1.07	1.05	1.04	1.06	1.04	1.03	1.00	1.02	1.03	0.85(H)
RWA45 – 75mm	0.22	0.38	0.56	0.73	0.85	1.13	1.15	1.24	1.22	1.16	1.11	1.09	1.08	1.08	1.08	1.08	1.09	1.10	1.00
RW3 - 40mm	0.05	0.07	0.19	0.31	0.44	0.63	0.80	0.97	1.04	1.04	1.08	1.05	1.08	1.03	1.04	1.00	1.01	1.00	0.75(MH)
RW3 - 50mm	0.09	0.13	0.28	0.43	0.63	0.84	0.93	1.12	1.13	1.08	1.09	1.10	1.08	1.06	1.06	1.05	1.01	1.02	0.95
RW3 - 75mm	0.17	0.40	0.59	0.85	0.98	1.13	1.19	1.21	1.20	1.15	1.10	1.05	1.06	1.04	1.08	1.07	1.06	1.09	1.00
RW4 – 30mm	0.03	0.04	0.09	0.18	0.29	0.46	0.58	0.84	0.94	0.96	1.0	1.03	1.07	1.02	1.04	1.0	1.01	1.04	0.6(MH)
RW4 – 50mm	0.11	0.12	0.37	0.47	0.63	0.90	1.0	1.13	1.13	1.12	1.09	1.08	1.02	1.05	1.02	1.03	1.03	1.03	0.95
RW4 – 75mm	0.24	0.40	0.67	0.82	1.01	1.15	1.16	1.20	1.16	1.11	1.11	1.08	1.04	1.06	1.08	1.12	1.08	1.05	1.00
RW5 - 30mm	0.03	0.03	0.11	0.19	0.30	0.50	0.62	0.85	0.97	1.01	1.03	1.05	1.05	1.04	1.04	1.04	1.03	1.02	0.65(MH)
RW5 - 50mm	0.14	0.14	0.36	0.58	0.74	0.94	1.02	1.12	1.14	1.10	1.04	1.02	1.02	1.03	1.05	1.01	1.04	1.05	1.00
RW5 - 75mm	0.27	0.44	0.74	0.97	0.95	0.99	1.07	1.15	1.10	1.03	1.07	1.04	1.07	1.05	1.06	1.07	1.08	1.05	1.00

All information, calculation, replies and/or specification contained herein is solely based upon the details supplied by you. It is the responsibility of the user to confirm the adequacy and accuracy of the information supplied. For the avoidance of doubt, you acknowledge and agree that Rockwool Limited ("Rockwool") have a very limited knowledge of the project in question and if the information you supply is not accurate then the information, calculation, replies and/or specification Rockwool provide herein will not be accurate as a result of such inaccurate information. Rockwool makes no representations nor gives any warranties of any kind as to the accuracy or completeness of the information, calculation, replies and/or specification provided by Rockwool's technical sales department. A MORE DETAILED VERSION OF THIS DISCLAIMER IS AVAILABLE ON OUR WEB SITE

Technical Sales Department. Rockwool Limited, Pencoed, Bridgend.  
CF35 6NY

## Absorption Coefficients of Rockwool Slabs



Noise absorption is the reduction in sound energy obtained when the sound is reflected from a surface. In general, the harder the surface, the more sound is reflected.

Noise absorption is expressed as a factor between 0 and 1.0. If a surface absorbs no sound, its coefficient of absorption is 0. If 100% of the sound is absorbed, the coefficient is 1.0 and if 50% then 0.50 and so on.

The structure of mineral wool in Rockwool makes it an ideal product for use as a sound absorber, with characteristically high coefficients over a wide frequency range.

The test used is the reverberation room method which gives a good rating assessment. Due to room differences and inherent material variations, measured absorption coefficients show wide variations and it is not practical to place reliance on differences in coefficients of less than 0.15.

When used as a sound absorbent lining within a room, the sound reduction that can be obtained usually ranges between 5 and 10dB. The actual reduction depends on the room details etc, and an assessment by an acoustic consultant should be obtained.

An appreciable airspace incorporated behind the acoustic slabs improves the low frequency sound absorption coefficient.

All information, calculation, replies and/or specification contained herein is solely based upon the details supplied by you. It is the responsibility of the user to confirm the adequacy and accuracy of the information supplied. For the avoidance of doubt, you acknowledge and agree that Rockwool Limited ("Rockwool") have a very limited knowledge of the project in question and if the information you supply is not accurate then the information, calculation, replies and/or specification Rockwool provide herein will not be accurate as a result of such inaccurate information. Rockwool makes no representations nor gives any warranties of any kind as to the accuracy or completeness of the information, calculation, replies and/or specification provided by Rockwool's technical sales department. A MORE DETAILED VERSION OF THIS DISCLAIMER IS AVAILABLE ON OUR WEB SITE

**Technical Sales Department. Rockwool Limited, Pencoed, Bridgend.**  
CF35 6NY  
[www.rockwool.co.uk](http://www.rockwool.co.uk)